PRODUCT SPECIFICATION SHEET



FLUORIDE & ORGANICS SELECTIVE BONE CHAR ADSORBANT

ResinTech SIR-950 is a specially manufactured bone char carbon. It is a granular activated carbonaceous material that has a unique combination of hydroxyapatite [Ca10(PO4)6(OH)2] and carbon. SIR-950 is intended for the removal of fluoride from water as well as the removal of heavy metals, taste and odor, and other contaminants commonly found in water.

APPLICATIONS

• Fluoride Removal

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Functional Group	Hydroxyapatite
Physical Form	Carbonaceous Granules
Particle Size	12 to 50 US Mesh (297 - 1680 μm)
% < 50 mesh (300μm)	< 1%
Temp Limit	212°F (100°C)
Color	Black
Uniform Particle Size	Yes

PACKAGING OPTIONS

- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks

SUGGESTED OPERATING CONDITIONS

Maximum temperature 140°F
Minimum bed depth 2 inches in filters
18 inches in tanks

Service flow rate*

Continuous flow 2 to 5 gpm/cu.ft. Intermittent flow 15 gpm/cu.ft.

Note: *To minimize possible bio growth, cartridges should be kept cool once wetted.

These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support

